

IN THE CLAIMS

1.-23. (canceled)

24. (currently amended) A composition for use in preparing a catalytically active solid, said composition comprising:

(A) water in a quantity sufficient to provide a shaped foraminous catalyst mixture;

(B) catalytically active metals useful in chemically refining hydrocarbons, said metals in the form of at least one component providing at least one metal from Group VIB of the periodic table and at least one component providing at least one metal from Group VIII of the periodic table, wherein the molar ratio of said Group VIII metal to Group VIB metal is about 0.05 to about 0.45, and wherein said Group VIII metal component is provided by a substantially water insoluble component; and

(C) at least one substantially water-soluble phosphorous-containing acidic component in an amount insufficient to solubilize said Group VIII metal at ambient temperature and sufficient to provide a phosphorous to Group VIB molar ratio of about 0.05 to about 0.25; and

(D) at least one uncalcined foraminous catalyst carrier, said carrier comprising agglomerates thereby resulting in a catalytically active solid exhibiting a macroporous structure.

25. (original) A composition according to claim 24 further comprising up to about 5 wt.% of an aqueous nitric acid component.

26. (original) A composition according to claim 24 wherein said Group VIII component is selected from the group consisting of a nickel carbonate and a cobalt carbonate.

27. (original) A composition according to claim 24 further comprising an additional amount of an element from Group VIII in the form of a substantially water soluble component.

28. (original) A composition according to claim 27 wherein the molar ratio of total Group VIII metal to Group VIB metal is about 0.05 to about 1.0.

29. (original) A composition according to claim 28 wherein the molar ratio of total Group VIII metal to Group VIB metal is about 0.20 to about 0.95.

30. (original) A composition according to claim 28 wherein the molar ratio of total Group VIII metal to Group VIB metal is about 0.30 to about 0.9.

31. (original) A composition according to claim 27 wherein said Group VIII component is a nickel nitrate.

32. (original) A composition according to claim 24 wherein said phosphorous-containing acidic component is orthophosphoric acid.

33. (original) A composition according to any one of claims 24 or 32 wherein said acidic component is present in an amount to provide a phosphorous to Group VIB molar ratio of about 0.05 to about 0.25.

34. (original) A composition according to claim 33 wherein said molar ratio of phosphorous to Group VIB metal is about 0.07 to about 0.23.

35. (original) A composition according to claim 34 wherein said molar ratio of phosphorous to Group VIB metal is about 0.08 to about 0.20.

36. (original) A composition according to claim 34 wherein said molar ratio of phosphorous to Group VIB metal is about 0.09 to about 0.18.

37. (original) A composition according to claim 26 wherein said Group VIII component is nickel carbonate.

38. (original) A composition according to any one of claims 24 through 32 and 37 wherein said Group VI metal is selected from molybdenum or tungsten.

39. (original) A composition according to claim 38 wherein said Group VI metal is molybdenum.

40. (original) A composition according to claim 24 wherein said molar ratio of Group VIII metal to Group VIB metal is about 0.05 to about 0.40.

41. (original) A composition according to claim 40 wherein said molar ratio is about 0.05 to about 0.30.

42. (original) A composition according to claim 40 wherein said molar ratio is about 0.10 to about 0.25.

43. (original) A composition according to claim 24 wherein the concentration of said Group VIB metal is at least about 3 to about 50 weight percent.

44. (original) A composition according to claim 24 wherein the concentration of said Group VIB metal is about 26 to about 46 weight percent.

45. (original) A composition according to claim 44 wherein the concentration of said Group VIB metal is at least about 28 to about 42 weight percent.

46. (original) A composition according to claim 24 wherein the concentration of said Group VIB metal is about 3 to about 6 weight percent.

47. (original) A composition according to claim 46 wherein the concentration of said Group VIB metal is at least about 3.5 to about 5.5 weight percent.

48. (original) A composition according to claim 43 wherein the concentration of said Group VIB metal is at least about 12 to about 48 weight percent.

49. (original) A composition according to any one of claims 24 through 32 and 37 wherein said foraminous catalyst carrier is at least one member selected from the group consisting of silica, silica-gel, silica-alumina, alumina, titania, titania-alumina, zirconia, boria, terrana, kaolin, magnesium silicate, magnesium carbonate, magnesium oxide, activated carbon, aluminum oxide, precipitated aluminum oxide, activated alumina, bauxite, kieselguhr, pumice, natural clays, synthetic clays, cationic clays or anionic clays such as saponite, bentonite, kaolin, sepiolite or hydrotalcite, and mixtures thereof.

50. (original) A composition according to any one of claims 24 through 32 and 37 wherein said foraminous catalyst carrier is selected from the group consisting of alumina, silica, silica-alumina, titania, titania-alumina, zirconia, natural clay, synthetic clay, and mixtures thereof.

51. (original) A composition according to claim 50 wherein said foraminous catalyst carrier is at least one member selected from the group consisting of silica, silica-alumina, alumina, natural clays, synthetic clays, and mixtures thereof.

Application No.: 10/719,551

Docket No.: W9652-01

52. (original) A composition according to claim 51 wherein said foraminous catalyst carrier is alumina.

53.-100. (canceled)